



INDIAN COARSE PUTTY

The ART of construction chemicals!



info@indianconstructionchemicals.in

Indian premium coarse putty is a WALL PUTTY specially developed as a base coat to cover unevenness and pinhole in plastered surfaces and to make the walls/ceilings ready for the final application of INDIAN PREMIUM COARSE. As is white, it can be treated as a base coat for putty. It contains the finest quality minerals, white cement, and premium quality polymers.



FEATURES:-

Excellent bonding to the base plaster/concrete

Can be used on new as well as old walls/ceilings

Water resistant

Reduction in cracking

Scratch resistant



ADVANTAGES:-

Excellence workability

Ease of use at site

Consistent work quality

Suitable for interiors as well as exteriors

Excellent, super smooth, super white finish



BENEFITS:-

Reduced putty consumption

Saves time

Cost effective



TECHNICAL DATA:-

PROPERTY	TYPICAL RESULTS
Colour	White
Pot life	60 minutes
PH	Alkaline
Coverage	Depends on finish of the wall
Recommended mixing ratio	300 – 400 ml water per kg of coarse putty
Recommended thickness	Not less than 2 mm to 3 mm

HOW TO APPLY:-

1 SURFACE PREPARATION

- Clean loose particles, dirt, grease, and traces of foreign material from the surface, if necessary, by using sand paper or by chipping
- For loose plaster areas, remove the defective material and re-plaster the area
- Fill up any cracks in base plaster by using INDIAN CRACK FILL

2 MIXING

- Take 6 – 8litres of clean water per 20 kg in a clean bucket. Add the required quantity of INDIAN PREMIUM COARSE PUTTY. Adjust the water to the amount of material used at a time.
- Stir continuously by using an electric mixer or by hand to obtain a homogeneous lump-free paste
- Allow the resultant paste to stand for about 10 minutes for the additives to dissolve
- Re-mix again for about 2 minutes. The mixture is now ready
- Use the mix within 60 minutes



3

APPLICATION

- Dampen the surface to be plastered with clean water. Allow excess water to drain off
- Using a steel trowel/blade, apply the above mix to a thickness of about 2 mm. Level and smoothen the surface. Cure the first coat lightly after it dries
- Apply the second coat after the first coat has fully dried and set. Cure the second coat lightly for two days
- The thickness of each coat should not be less than 2 mm
- Smoothen with a steel trowel. Sandpaper if so desired, with 300 no. sandpaper

PRECAUTIONS:

INDIAN PREMIUM COARSE PUTTY contains only eco-friendly fillers and additives. However, being white cement-based, it is alkaline and hence it is advisable to avoid direct eye and skin contact with this. In case of eye contact, flush with clean water at least for 15 minutes and seek medical help.

PACKING AND STORAGE

INDIAN PREMIUM COARSE PUTTY is supplied in **20 kg** bags and has a shelf life of 1 year if stored in a cool and dry location.

